

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

REQUEST FOR ACCESS TO AN ABANDONED APPLICATION UNDER 37 CFR 1.14Bring completed form to
File Information Unit, Room 2E04
2900 Crystal Drive
Arlington, VA 22202-3514

Telephone: (703) 308-2733

In re Application of

Application Number

09/063924

Filed

April 22, 1998

Paper No. #12

I hereby request access under 37 CFR 1.14(a)(1)(iv) to the application file record of the above-identified ABANDONED application, which is not within the file jacket of a pending Continued Prosecution Application (CPA) (37 CFR 1.53(d)) and which is identified in, or to which a benefit is claimed, in the following document (as shown in the attachment):

United States Patent Application Publication No. _____, page, _____ line _____.

United States Patent Number 6090178, column _____, line, _____ or

WIPO Pub. No. _____, page _____, line _____.

Related Information About Access to Applications Maintained in the Image File Wrapper System (IFW) and Access to Pending Applications in General

A member of the public, acting without a power to inspect, cannot order applications maintained in the IFW system through the FIU. If the member of the public is entitled to a copy of the application file, then the file is made available through the Public Patent Application Information Retrieval system (Public PAIR) on the USPTO internet web site (www.uspto.gov). Terminals that allow access to Public PAIR are available in the Public Search Room. The member of the public may also be entitled to obtain a copy of all or part of the application file upon payment of the appropriate fee. Such copies must be purchased through the Office of Public Records upon payment of the appropriate fee (37 CFR 1.19(b)).

For published applications that are still pending, a member of the public may obtain a copy of:

the file contents; the pending application as originally filed; or any document in the file of the pending application.

For unpublished applications that are still pending:

- (1) If the benefit of the pending application is claimed under 35 U.S.C. 119(e), 120, 121, or 365 in another application that has: (a) issued as a U.S. patent, or (b) published as a statutory invention registration, a U.S. patent application publication, or an international patent application publication in accordance with PCT Article 21(2), a member of the public may obtain a copy of: the file contents; the pending application as originally filed; or any document in the file of the pending application.
- (2) If the application is incorporated by reference or otherwise identified in a U.S. patent, a statutory invention registration, a U.S. patent application publication, or an international patent application publication in accordance with PCT Article 21(2), a member of the public may obtain a copy of the pending application as originally filed.

Darlene Jones

Signature

Darlene Jones

Typed or printed name

Registration Number, if applicable

703-418-0330

Telephone Number

FOR PTO USE ONLY

Approved by:

(initials)

Unit:

This collection of information is required by 37 CFR 1.11 and 1.14. The information is required to obtain or retain a benefit by the public which is to file (and by the USPTO to process) an application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.11 and 1.14. This collection is estimated to take 12 minutes to complete, including gathering, preparing, and submitting the completed application form to the USPTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. **BRING TO: File Information Unit, Room 2E04, 2900 Crystal Drive, Arlington, Virginia.**

If you need assistance in completing the form, call 1-800-PTO-9199 and select option 2.

United States Patent

[19]

Benini

[11] Patent Number:

6,090,178

[45] Date of Patent:

Jul. 18, 2000

[54] FRANGIBLE METAL BULLETS,
AMMUNITION AND METHOD OF MAKING
SUCH ARTICLES

[75] Inventor: Joseph C. Benini, Kersey, Pa.

[73] Assignee: SinterFire, Inc., Kersey, Pa.

[21] Appl. No.: 09/186,366

[22] Filed: Nov. 5, 1998

Related U.S. Application Data

[62] Division of application No. 09/063,924, Apr. 22, 1998,
abandoned.

[51] Int. Cl.⁷ B22F 3/02

[52] U.S. Cl. 75/245; 75/247; 102/517;
419/2; 419/44

[58] Field of Search 75/245, 246, 247;
419/44; 102/517

References Cited

U.S. PATENT DOCUMENTS

2,409,307 10/1946 Patch et al.
3,123,003 3/1964 Lange, Jr. et al.
3,216,358 11/1965 Findelsen
3,338,167 8/1967 Jungermann et al.
3,439,619 4/1969 Bock et al.
3,951,035 4/1976 Dautzenberg et al.
4,112,846 9/1978 Gilbert et al.
4,850,378 7/1989 Dinkha et al. 102/501

4,958,572 9/1990 Martel 102/529
5,078,054 1/1992 Ashok et al. 102/517
5,237,930 8/1993 Bélanger et al. 102/529
5,399,187 3/1995 Mravic et al. 75/228
5,616,642 4/1997 West et al. 524/439
5,665,808 9/1997 Bilsbury et al. 524/439
5,679,920 10/1997 Hallis et al. 102/506

OTHER PUBLICATIONS

SCM Metal Products, Inc. Brochure, "Premixed Bronze
Powders for P/M Bearings," (1996).

Primary Examiner—Ngoclan Mai

Attorney, Agent, or Firm—Finnegan, Henderson, Farabow,
Garrett & Dunner, LLP

[57]

ABSTRACT

A frangible metal bullet, a method for making it, and ammunition made therefrom. The frangible metal bullet is formed from a mixture of metal particles and metal or metalloid binder forming material which is compacted into the desired shape, heated to a temperature above that needed to form at least one intermetallic compound but below the temperature of joining of the metal particles by sintering and below the temperature of formation of substantial amounts of a ductile alloy of the metal of the particles and the metal or metalloid binder forming material and then cooled. Such bullets have sufficient strength to maintain their integrity during firing but disintegrate into powder on impact and can be formulated to be lead-free.

23 Claims, 1 Drawing Sheet



US006090178A

United States Patent [19]**Benini**[11] **Patent Number:** **6,090,178**[45] **Date of Patent:** **Jul. 18, 2000**[54] **FRANGIBLE METAL BULLETS,
AMMUNITION AND METHOD OF MAKING
SUCH ARTICLES**[75] **Inventor:** **Joseph C. Benini, Kersey, Pa.**[73] **Assignee:** **SinterFire, Inc., Kersey, Pa.**[21] **Appl. No.:** **09/186,366**[22] **Filed:** **Nov. 5, 1998****Related U.S. Application Data**[62] Division of application No. 09/063,924, Apr. 22, 1998,
abandoned.[51] **Int. Cl.⁷** **B22F 3/02**[52] **U.S. Cl.** **75/245; 75/247; 102/517;
419/2; 419/44**[58] **Field of Search** **75/245, 246, 247;
419/44; 102/517**[56] **References Cited****U.S. PATENT DOCUMENTS**

2,409,307 10/1/946 Patch et al. .
 3,123,003 3/1/964 Lange, Jr. et al. .
 3,216,358 11/1/965 Findeisen .
 3,338,167 8/1/967 Jungermann et al. .
 3,439,619 4/1/969 Bock et al. .
 3,951,035 4/1/976 Dautzenberg et al. .
 4,112,846 9/1/978 Gilbert et al. .
 4,850,378 7/1/989 Dinkha et al. 102/501

4,958,572 9/1990 Martel 102/529
 5,078,054 1/1992 Ashok et al. 102/517
 5,237,930 8/1993 Bélanger et al. 102/529
 5,399,187 3/1995 Mravic et al. 75/228
 5,616,642 4/1997 West et al. 524/439
 5,665,808 9/1997 Bilsbury et al. 524/439
 5,679,920 10/1997 Hallis et al. 102/506

OTHER PUBLICATIONSSCM Metal Products, Inc. Brochure, "Premixed Bronze
Powders for P/M Bearings," (1996).*Primary Examiner*—Ngoclan Mai*Attorney, Agent, or Firm*—Finnegan, Henderson, Farabow,
Garrett & Dunner, LLP[57] **ABSTRACT**

A frangible metal bullet, a method for making it, and ammunition made therefrom. The frangible metal bullet is formed from a mixture of metal particles and metal or metalloid binder forming material which is compacted into the desired shape, heated to a temperature above that needed to form at least one intermetallic compound but below the temperature of joining of the metal particles by sintering and below the temperature of formation of substantial amounts of a ductile alloy of the metal of the particles and the metal or metalloid binder forming material and then cooled. Such bullets have sufficient strength to maintain their integrity during firing but disintegrate into powder on impact and can be formulated to be lead-free.

23 Claims, 1 Drawing Sheet

United States Patent [19]

Benini

[11] Patent Number: 6,090,178

[45] Date of Patent: Jul. 18, 2000

[54] FRANGIBLE METAL BULLETS,
AMMUNITION AND METHOD OF MAKING
SUCH ARTICLES

[75] Inventor: Joseph C. Benini, Kerscy, Pa.

[73] Assignee: SinterFire, Inc., Kerscy, Pa.

[21] Appl. No.: 09/186,366

[22] Filed: Nov. 5, 1998

Related U.S. Application Data

[62] Division of application No. 09/063,924, Apr. 22, 1998,
abandoned.

[51] Int. Cl.⁷ B22F 3/02

[52] U.S. Cl. 75/245; 75/247; 102/517;
419/2; 419/44

[58] Field of Search 75/245, 246, 247;
419/44; 102/517

[56] References Cited

U.S. PATENT DOCUMENTS

2,409,307 10/1946 Patch et al. .
3,123,003 3/1964 Lange, Jr. et al. .
3,216,358 11/1965 Findeisen .
3,338,167 8/1967 Jungermann et al. .
3,439,619 4/1969 Bock et al. .
3,951,035 4/1976 Dautzenberg et al. .
4,112,846 9/1978 Gilbert et al. .
4,850,378 7/1989 Dinkha et al. 102/501

4,958,572 9/1990 Martel 102/529
5,078,054 1/1992 Ashok et al. 102/517
5,237,930 8/1993 Bélanger et al. 102/529
5,399,187 3/1995 Mravic et al. 75/228
5,616,642 4/1997 West et al. 524/439
5,665,808 9/1997 Bilsbury et al. 524/439
5,679,920 10/1997 Hallis et al. 102/506

OTHER PUBLICATIONS

SCM Metal Products, Inc. Brochure, "Premixed Bronze
Powders for P/M Bearings," (1996).

Primary Examiner—Ngoclan Mai
Attorney, Agent, or Firm—Finnegan, Henderson, Farabow,
Garrett & Dunner, LLP

[57] ABSTRACT

A frangible metal bullet, a method for making it, and ammunition made therefrom. The frangible metal bullet is formed from a mixture of metal particles and metal or metalloid binder forming material which is compacted into the desired shape, heated to a temperature above that needed to form at least one intermetallic compound but below the temperature of joining of the metal particles by sintering and below the temperature of formation of substantial amounts of a ductile alloy of the metal of the particles and the metal or metalloid binder forming material and then cooled. Such bullets have sufficient strength to maintain their integrity during firing but disintegrate into powder on impact and can be formulated to be lead-free.

23 Claims, 1 Drawing Sheet

Do
Not
Need

Pls
Ret

Do
Not
Need